



# Technical Data Sheet

## Giorgio Graesan SPIRITO LIBERO

Effective from 30 May 2019

### Description

Giorgio Graesan Spirito Libero is a fine grained lime plaster that can be used on internal surfaces. It is naturally resistant to mould and bacteria and is an excellent choice for areas of high humidity such as bathrooms and laundries. It easy to apply and can be tinted with mineral pigment to achieve a range of colours. Giorgio Graesan recommend that our entire range of lime based natural materials are used only by highly skilled and licensed tradespeople with extensive experience in this field. It is the responsibility of the applicator to understand the application method and the procedure involved, in order to obtain a satisfactory outcome.

### Uses

Suitable for interior use

Can be applied over any standard building substrate following correct surface preparation

### Colour

White to off-white colour. Can be tinted using Giorgio Graesan Tints. When tinting the product it is recommended that the coloured product be left to rest for a minimum of 12 hours before applying to surfaces

### Sheen Level

Flat finish

### Coverage Rate

1-1.2kg/2 overall applied in 2 coats

### Application Method

Steel Trowel

### Typical Data at 25°C and 50% Relative Humidity

Drying Time	12 hours
Touch Dry	2 hours
Curing Time	28 days
Usual No of Coats	Two coats



# Technical Data Sheet

## Giorgio Graesan SPIRITO LIBERO

Effective from 30 May 2019

Clean Up	Water
Packaging Sizes	24 kg, 8 kg, 2 kg
Abrasion Resistance	Very Good
Water Resistance	Excellent

**Pot Life** Once opened, use within 12 months. Store in a cool, dry and well ventilated place, away from sources of heat and from direct sunlight

### Substrate Conditions

Substrate must be installed as per manufacturer's specifications prior to application

Substrate must be clean and free of dust, dirt, oil, salt, mould or any other contamination

Any base coats should be fully cured

For full details on application for each substrate refer to the Giorgio Graesan Specification and System Guide

### Mixing

Spirito Libero is pre mixed and comes ready to use. Product will need to be mixed thoroughly before use.

### Application

Before applying SPIRITO LIBERO it is recommended that surface be prepared with Giorgio Graesan Primus Naturale. Primer to be applied with a roller in an even coat

Apply 1<sup>st</sup> coat of Spirito Libero with a steel trowel, ensuring full, even coverage of the surface area approximately 0.6 mm thick.

Allow 24 hours drying time before applying 2<sup>nd</sup> coat wet-on wet application approximately 0.6 mm in thickness, trowel to desired finish



# Technical Data Sheet

## Giorgio Graesan SPIRITO LIBERO

Effective from 30 May 2019

### Precautions and Limitations

Adequate PPE should be used when mixing and applying product

Do not apply if the temperature will fall below 5°C or above 35°C during application.

Do not apply in direct sunlight, wind or rain and protect the finished work until fully cured

### Transport and Storage

Store in a cool, dry place

Keep pail sealed when not in use

### Disposal

Dispose of in accordance with local council regulations

### Safety Data

Refer to Giorgio Graesan Spirito Libero SDS

Giorgio Graesan will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, Giorgio Graesan Australia reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.



GIORGIO GRAESAN  
and Friends - Australia

# Technical Data Sheet

## Giorgio Graesan SPIRITO LIBERO

Effective from 30 May 2019